



CHUKOH FLOTM Adhesive tape

ASF-119T

OUTLINE

This tape consists of an embossed fluororesin (PTFE) film and coated with a silicone adhesive. Its slipperiness is 30% better than ASF-110FR, and its release properties are also improved.

CHARACTERISTICS //

- ·Heat resistance
- ·Lowest friction
- Non-stick property
- ·Chemical resistance
- · Electric insulation
- ·Water repellency
- Cushioning
- Cleanliness

APPLICATIONS //


- ·Improves the slipperiness of transported items
- Prevent the products from scratches
- Prevents adhesion of sticky substances (such as unvulcanized rubber)

PERFORMANCE

Test item	Unit	ASF-119T	
Total thickness	mm	0.35	
Adhesion/180° peel test	N/25mm	8	
Tensile strength	N/25mm	_	
Breakdown voltage	kV	12	
Maximum service temperature	℃	200	

^{*}Values shown in this table represent measurements and do not constitute guaranteed values.

COMPOSITION



SURFACE ENLARGED



SPECIFICATION //

Total thickness	Width (mm)		Longth
(mm)	Standard products	Maximum width	Length (m)
0.35	25, 50	250	10

^{*}Tapes can be slit to widths not shown above up to the maximum width.

Chukoh Chemical Industries, Ltd.

To Contact us:

AKASAKA INTERCITY AIR 26F, 1-8-1, Akasaka, Minato-ku, Tokyo 107-0052 Japan Tel: +81-(0)3-6230-4424, Fax: +81-(0)3-6230-4446

AKASAKA INTERCITY AIR 26F, 1-8-1, ■Head Quarters Akasaka, Minato-ku, Tokyo 107-0052 Japan

Tel: +81-(0)3-6230-4414, Fax: +81-(0)3-6230-4413

Support mail: support@chukoh.co.jp



- Do not use for medical applications or other usages involving a contact with human body.
 Observe the related laws and regulations for disposal. Do not incinerate in any case.
- Do not use at the temperature exceeding the maximum service temperature.
- Please read the catalogue and product safety data sheet (SDS) on our website to maintain the original functions of product and ensure safe use